



THERMAFIBER® RAINBARRIER® CI HIGH COMPRESSIVE (80) MINERAL WOOL INSULATION

Thermafiber[®] RainBarrier[®] ci High Compressive (80) continuous insulation boards are designed to support cladding attachment with minimal penetrations. The use of ThermaCrimp[™] technology allows for excellent compressive strength while providing thermal efficiency, non-combustibility, water repellency, and flexibility when working with uneven substrates. RainBarrier[®] ci High Compressive (80) can be used behind light weight cladding – including combustible and open-joint assemblies.

Features

- High compressive strength to support cladding attachment system with minimal penetration through continuous insulation
- More than 10% lighter in weight than the leading competitor's product
- Vapor permeable
- Tolerant of substrate irregularities
- Non-combustible and non-deteriorating
- Fire resistant to temperatures above 2,000°F (1,093°C)
- Enhances acoustical performance
- Minimum 70% recycled content¹
- Contributes to credits in several green building programs such as LEED® and Green Globes®

Standards, Codes Compliance

• ASTM C612, Mineral Fiber Block and Board Thermal Insulation, Types IA, IB, II, III, IVA, IVB

Technical Data

TESTED TO ASTM C518

| "k" @ 75º [24ºC] BTU.in/hr. sq. ft. ºF | "R" value per inch of thickness ² |
|--|--|
| 0.24 | 4.2 |

2 R = thickness divided by "k"

Acoustical Performance

| | THICKNESS | 125 HZ | 250 HZ | 500 HZ | 1000 HZ | 2000 HZ | 4000 HZ | NRC |
|--------------|-----------|--------|--------|--------|---------|---------|---------|------|
| ASTM C423 | 2" | 0.22 | 0.90 | 1.05 | 1.06 | 1.02 | 1.04 | 1.00 |

Physical Properties

| PROPERTY | TEST METHOD | VALUE |
|--|-------------|--------------------------------------|
| Compressive Strength | ASMT C165 | 475 lbs/ft² @ 10% deformation |
| Corrosion of Steel, Aluminum, and Copper | ASTM C665 | Pass |
| Stress Corrosion – Austenitic Stainless Steel | ASTM C795 | Pass |
| Combustibility | ASTM E136 | Non-combustible |
| Water Vapor Permeance | ASTM E96 | 24 perm |
| Water Vapor Sorption | ASTM C1104 | Sorption <0.1% by volume |
| Linear Shrinkage | ASTM C356 | <2% @1,200°F (650°C) |
| Surface Burning Characteristics | ASTM E84 | Flame Spread 0, Smoke Developed 0 |
| Fungi-Resistance | ASTM C1338 | Complies |
| Odor | ASTM C1304 | Complies |

Availability

| THICKNESS ³ | WIDTHS | LENGTHS |
|------------------------|----------|----------|
| 1.5"-4" | 24", 48" | 48", 72" |

3 Thicknesses are available in 1/2" increments

Installation

Thermafiber, Inc. recommends mechanical attachment of Thermafiber® RainBarrier® insulation products. See Owens Corning publication "Thermafiber® RainBarrier® Continuous Insulation Guide" (Pub. No. 10021356) for more information.

Product Options

Recycled Content Options^{1,4}:

- EPA Choice Fiber (U.S. Government Buildings)Minimum 75%
 Standard Fiber70%
- 4 Recycled content options other than standard must be specified at time of order.

Environmental and Sustainability

Owens Corning is a worldwide leader in building material systems, insulation and composite solutions, delivering a broad range of high quality products and services.

Owens Corning is committed to driving sustainability by delivering solutions, transforming markets and enhancing lives. More information can be found at www.owenscorning.com.

Certifications and Sustainable Features

- ¹Verified by ICC-ES to contain a minimum of 70% recycled content. See ICC-ES Evaluation Report VAR-1025 at icc-es.org.
- Environmental Product Declaration (EPD) has been certified by UL Environment. For more information visit ul.com/epd.
- Rainbarrier[®] Products have a published Health Product Declaration (HPD).



Disclaimer of Liability

Thermafiber, Inc. shall not be liable for incidental and consequential damages, directly or indirectly sustained, nor for any loss caused by application of these goods not in accordance with current printed instructions or for other than the intended use. Thermafiber, Inc. liability is expressly limited to replacement of defective goods. Any claim shall be deemed waived unless made in writing within thirty (30) days from date it was or reasonably should have been discovered.

UL and the UL logo are trademarks of UL LLC.

Notes

For additional information, refer to the Safe Use Instruction Sheet (SUIS) found in the SDS Database via http://sds.owenscorning.com.

THERMAFIBER, INC. ONE OWENS CORNING PARKWAY TOLEDO, OHIO, USA 43659

888-TFIBER1 [834-2371] www.owenscorning.com/thermafiber