## **Technical Datasheet**

Meltell<sup>®</sup> 310 white Meltell<sup>®</sup> 320 black Meltell<sup>®</sup> 330 grey

| Updated on:          | March 22, 2021   |
|----------------------|--|
| Distributor:         | SIGA Canada Inc.   |
| Type of application: | Sealing of joint connections for windows, doors and facades, leakages, cracks and penetrations indoors and outdoors            |
| Packaging unit:      | 20 cartridges / box<br>12 sausages / box   |
| Composition:         | 1-component hybrid polymer sealant.<br>Solvent- and isocyanate-free, low odour, can be painted and varnished.                  |
|                      | <ul> <li>ASTM C 920, Type S, Grade NS, Class 25, Use NT,<br/>Mortar (M), Anodized Aluminum (A), Vinyl (O), Wood (W)</li> </ul> |

✓ CAN/CGSB-19.13-M87

| Property                |                                 | Standards  | Unit                 | Values                                   |
|-------------------------|---------------------------------|------------|----------------------|--|
| Packaging               | Cartridge                       |            | fl.oz (mL)           | 10.48 (310)                              |
|                         | Tubular bag                     |            |                      | 20.28 (600)                              |
| Colour                  |                                 |            |                      | black / grey<br>/white                   |
| Density                 | at 23° C                        |            | [g/cm <sup>3</sup> ] | 1.5                                      |
| Temperature resistance  |                                 |            | °F<br>℃              | -40 °F to +194<br>°F<br>-40 °C to +90 °C |
| Application temperature |                                 |            | °F<br>℃              | 14 °F to +104 °F<br>-10 °C to + 40<br>°C |
| Movement capability     |                                 | ASTM C 719 | %                    | ±25                                      |
| Rheological             | Sag in vertical displacement    | ASTM C 639 |                      | No sag                                   |
| Hardness                | Shore A, at standard conditions | ASTM C 661 |                      | 16                                       |
| Weight loss             | After heat aging                | ASTM C1246 | %                    | 1.1                                      |

## Characteristics:

| Tack-Free Time                    |   | ASTM C 1246               | :   | 110                       |  |
|-----------------------------------|---|---------------------------|-----|---------------------------|--|
| Stain and color change            |   | ASTM C 1246               | min | Pass<br>(No visible stain |  |
| Bond durability                   |   | ASTM C 719                |     | or color change)<br>Pass  |  |
| Adhesion-in-Peel                  | Mortar unprimed   | ASTM C 794                | lbf | 19                        |  |
|                                   | Anodized Aluminum<br>unprimed   |                           | lbf | 31                        |  |
| Effects of accelerated weathering | After accelerated weathering  | ASTM C 794/<br>ASTM C1442 |     | Pass                      |  |
|                                   | After cold exposure<br>and low temperature<br>bend  |                           |     | Pass                      |  |
| Skin formation time               | at 23°C/50% rLf   |                           | min | 20-30                     |  |
| Curing/drying-through in 24h      | at 23°C/50% rLf   |                           | mm  | 2-3                       |  |
| Prerequisite for a secure bond    | Substrates must be dust and grease-free and non-repelling. Clean substrates and test adhesion before bonding. |                           |     |                           |  |
| Shelf life                        | 12 months when properly stored  |                           |     |                           |  |

SIGA Hee